

// 076EH


Oxygen/acetylene twin welding 20 bar (300 psi)
EN ISO 3821

Tube: black SBR.

Reinforcement: high tensile textile cords.

Cover: blue, red SBR/EPDM - abrasion and ozone resistant.

Application: oxygen/acetylene twin welding.

Constant operation: -25 °C +80 °C (-13 °F +176 °F)

↔		↔		↻		↻		⤴		⚖		
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
6,0	1/4"	13,00	0,51	20	300	60	900	80,0	3,15		0,360	0,25
8,0	5/16"	15,00	0,59	20	300	60	900	80,0	3,15		0,410	0,28
10,0	3/8"	17,00	0,67	20	300	60	900	100,0	3,94		0,500	0,34

// 076EI


Oxygen/LPG twin welding 20 bar (300 psi)
EN ISO 3821

Tube: black SBR.

Reinforcement: high tensile textile cords.

Cover: blue, orange SBR/EPDM - abrasion and ozone resistant.

Application: oxygen/LPG twin welding.

Constant operation: -30 °C +80 °C (-22 °F +176 °F)

↔		↔		↻		↻		⤴		⚖		
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
8,0	5/16"	15,00	0,59	20	300	60	900	80,0	3,15		0,400	0,27